



Technical Data Sheet

Chemmot Ewa & Jerzy Kumorek spółka jawna
PL 32-050 Skawina, ul. Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Trade name

DECORATION by DECO COLOR® aerosol line

Article No

10000; 10001; 10010; 10011; 10020; 10021; 10030; 10031; 10032; 10040; 10050; 10060;
10061; 10070; 10071; 10072; 10080; 10090; 10100; 10101; 10110; 10120; 10121; 10122;
10123; 10124; 10125; 10130; 10131; 10140; 10150; 10160; 10170; 10180; 10190; 10195;
10200

Seller/Manufacturer

Chemmot Ewa & Jerzy Kumorek spółka jawna; Piłsudskiego 59, 32-050 Skawina, Polska

Product's description

Universal synthetic solvent-based lacquer for painting surfaces made of metal, wood, ceramics, glass, wicker, cardboard, fabrics, fresh and artificial flowers, and some plastics. Wide range of application hobby and professional works: at home, garden, automotive and industry. Especially practical for works of art and decoration.

Main features

Very good coverage of the painted surface
High gloss
High resistance to abrasion and weather conditions
Variety of colours: 35 most popular colours in RAL system
For indoor and outdoor use
CFC free

Physical and Chemical Properties

Capacity	400 ml
Base/resin	alkyd
Colour	RAL numbers
Gloss	high gloss / mat
Application temperature	15-25°C
Dust free	10-15 min
Touch free	30-40 min
Hardened	after 24 h
Cover capacity	1,5-2 m ² depending on colour and type of surface by one application
High temperature resistance	up to 120°C
VOC content	about 80%
Solids content	about 20%
Petrol resistance	good
Alcohol resistance	moderate
Primer usage	recommended compatible DECO COLOR primers usage
Other coating applying	not recommended



Technical Data Sheet

Chemmot Ewa & Jerzy Kumorek spółka jawna
PL 32-050 Skawina, ul. Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Usage

Before application read carefully instructions on the container and use according to the manufacturer's recommendations.

Recommended substrate conditions

Proper surface preparation has huge influence to final result. Fundamental principle, which relate to all surfaces prepared to painting is to grind, degrease and let it dry.
Primed surface should be grinded with fine-grained abrasive paper previously.
Notice. For surfaces made of PUR, PS, PA, EPDM, ABS, GfK, Hart – PCV use Plastic Primer DECO COLOR previously.

Method of use

Apply product at temperature about 15-25°C (optimum temperature for good varnish drying).
Drying time depends also on air humidity and product density.
Painting should be made in well ventilated room.
Prior to commencing painting, shake the container for about one minute, what helps mix the varnish by the ball inside.
Perform the test spray.
Apply the varnish with few thin layers rather than one thick layer, from the distance of 25-30 centimetres.
Wait few minutes between each layer when applying.
When finished, clean the nozzle.
Put the container upside down, pressing the nozzle for the period of three seconds.

Technical Data Sheet version 04 from 25/03/2014