



Karta techniczna produktu

Chemmot Ewa Kumorek spółka komandytowa
PL 32-050 Skawina, ul. Józefa Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Trade name	
MASTICAR by DECO COLOR® aerosol line	
Article No	
27 551	
Seller/Manufacturer	
Chemmot Ewa Kumorek spółka komandytowa; Józefa Piłsudskiego 59, 32-050 Skawina, Polska	
Product's description	
<p>Underbody car's protection on bitumen base. Suitable for wood, metal, concrete devices, as well as constructions on and under the ground. Notice. It can be applied on raw surfaces and also when primed and painted previously.</p>	
Main features	
<p>Stops corrosion process Perfect adhesion to smooth surfaces as well as previously primed and painted. Creates strong adhesive, waterproof and elastic protective layer. Sound absorbing properties – protects against stone hits Protects against adverse factors (water, salt) Waterproof For indoor and outdoor use CFC free</p>	
Physical and Chemical Properties	
Capacity	500 ml
Base/resin	petroleum resins
Application temperature	15-25°C
Dust free	5-10 min
Touch free	15-25 min
Hardened	6 h
Cover capacity	3 m ²
High temperature resistance	up to 80°C
VOC content	about 70%
Solids content	about 30%
Petrol resistance	good
Alcohol resistance	good
Primer usage	not recommended
Other coating applying	not possible



Karta techniczna produktu

Chemmot Ewa Kumorek spółka komandytowa
PL 32-050 Skawina, ul. Józefa Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Usage

Before application read carefully instructions on the container and use according to the manufacturer's recommendations.

Recommended substrate conditions

Proper surface preparation has huge influence to final result. Fundamental principle, which relate to all surfaces prepared to painting is to grind, degrease and let it dry.

Method of use

Apply product at temperature about 15-25°C (optimum temperature for good varnish drying).
Drying time depends also on air humidity and product density.
Painting should be made in well ventilated room.
Prior to commencing painting, shake the container for about one minute, what helps mix the varnish by the ball inside.
Perform the test spray.
Apply the varnish with few thin layers rather than one thick layer, from the distance of 25-30 centimetres.
Wait few minutes between each layer when applying.
When finished, clean the nozzle.
Put the container upside down, pressing the nozzle for the period of three seconds.

Technical Data Sheet version 05 from 01/03/2022