



# Karta techniczna produktu

Chemmot Ewa Kumorek spółka komandytowa  
PL 32-050 Skawina, ul. Józefa Piłsudskiego 59

Telefon: 12 276 75 45  
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®  
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

<b>Trade name</b>	
MOVICAR by DECO COLOR® aerosol line	
<b>Article No</b>	
27 581	
<b>Seller/Manufacturer</b>	
Chemmot Ewa Kumorek spółka komandytowa; Józefa Piłsudskiego 59, 32-050 Skawina, Polska	
<b>Product's description</b>	
Product for anticorrosive protection of all hollow spaces such as doors, thresholds, flaps racks, or engine lids. Used for water engines, motorboat parts, yachts, scooters, industrial machines, household appliances, to protect against corrosion of metals and steel dring storage and transport. Improves standard maintenance. Good supplement for protection after car's body repair and painting.	
<b>Main features</b>	
Creates highly adhesive, waterproof and elastic film in yellow colour Connects to rust, displaces it and stops corrosion from inside Stops corrosion process Excellent penetrating properties Effectively displaces water and moisture CFC free	
<b>Physical and Chemical Properties</b>	
Capacity	500 ml
Base/resin	wax
Colour	yellow
Gloss	high gloss / mat
Application temperature	15-25°C
Dust free	20-30 min
Touch free	n/a
Hardened	n/a
Cover capacity	3 m <sup>2</sup>
High temperature resistance	up to 80°C
VOC content	about 85%
Solids content	about 15%
Petrol resistance	n/a
Alcohol resistance	n/a



# Karta techniczna produktu

Chemmot Ewa Kumorek spółka komandytowa  
PL 32-050 Skawina, ul. Józefa Piłsudskiego 59

Telefon: 12 276 75 45  
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®  
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

## Usage

Before application read carefully instructions on the container and use according to the manufacturer's recommendations.

## Recommended substrate conditions

Proper surface preparation has huge influence to final result. Fundamental principle, which relate to all surfaces prepared to painting is to grind, degrease and let it dry.  
Primed surface should be grinded with fine-grained abrasive paper previously.  
Notice. For surfaces made of PUR, PS, PA, EPDM, ABS, GfK, Hart – PCV use Plastic Primer DECO COLOR previously.

## Method of use

Apply product at temperature about 15-25°C (optimum temperature for good varnish drying).  
Drying time depends also on air humidity and product density.  
Painting should be made in well ventilated room.  
Prior to commencing painting, shake the container for about one minute, what helps mix the varnish by the ball inside.  
Perform the test spray.  
Apply to difficult spots using soft applicator attached to the product. Suitable length (40cm) and special spray head, allows perfect application, and penetration in the slots of hollow spaces.  
When finished, clean the nozzle.  
Put the container upside down, pressing the nozzle for the period of three seconds.

**Technical Data Sheet version 05 from 01/03/2022**