



Karta techniczna produktu

Chemmot Ewa Kumorek spółka komandytowa
PL 32-050 Skawina, ul. Józefa Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Trade name	
RENOVATOR KALORYFER by DECO COLOR® aerosol line	
Article No	
30 470	
Seller/Manufacturer	
Chemmot Ewa Kumorek spółka komandytowa; Józefa Piłsudskiego 59, 32-050 Skawina, Polska	
Product's description	
Fast drying acrylic lacquer for painting and renovation of radiators made of steel and cast iron, central heating systems, pipes, boilers etc. Resistant to moisture. Doesn't become yellow, good thermal conductivity, fast drying. Provides smooth, durable surface, you can easily clean.	
Main features	
Heat resistance up to 100°C Resistant to moisture and rust Creates smooth, glossy surface Most popular colour: RAL 9016 Fast drying time: 5 minutes! Very good coverage of the painted surface Anticorrosive properties Hard acrylic film resistant to water and abrasion For indoor and outdoor use Capacity 400 ml	
Physical and Chemical Properties	
Capacity	400 ml
Base/resin	acrylic modified resin
Colour	RAL 9016
Gloss	high gloss
Application temperature	15-25°C
Dust free	5 min
Touch free	15-20 min
Hardened	16-20 h
Cover capacity	1,5-2 m ² by one application
High temperature resistance	up to 100°C
VOC content	about 80%
Solids content	about 20%
Petrol resistance	good
Alcohol resistance	insufficient
Primer usage	recommended compatible DECO COLOR primers usage
Other coating applying	possible



Karta techniczna produktu

Chemmot Ewa Kumorek spółka komandytowa
PL 32-050 Skawina, ul. Józefa Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Usage

Before application read carefully instructions on the container and use according to the manufacturer's recommendations.

Recommended substrate conditions

Proper surface preparation has huge influence to final result. Fundamental principle, which relate to all surfaces prepared to painting is to grind, degrease and let it dry.
Primed surface should be grinded with fine-grained abrasive paper previously.

Method of use

Apply product at temperature about 15-25°C (optimum temperature for good varnish drying).
Drying time depends also on air humidity and product density.
Painting should be made in well ventilated room.
Prior to commencing painting, shake the container for about one minute, what helps mix the varnish by the ball inside.
Perform the test spray.
Apply the varnish with few thin layers rather than one thick layer, from the distance of 25-30 centimetres.
Wait few minutes between each layer when applying.
When finished, clean the nozzle.
Put the container upside down, pressing the nozzle for the period of three seconds.

Technical Data Sheet version 05 from 01/03/2022